ORIGINAL ARTICLE

Additive Manufacturing with Liquid Latex and Recycled End-of-Life Rubber

Miguel A. Quetzeri-Santiago,^{1,*} Clara L. Hedegaard,^{1,*} and J. Rafael Castrejón-Pita¹

Abstract

Elastomers and rubber are common industrial materials used for test objects, supporting parts, and many other commercial products. The industrial processing of these materials is currently dominated by injection molding, which reduces manufacturing costs and speeds up production. However, this manufacturing method does not permit personalization or customization and lacks the versatility of other techniques such as three-dimensional printing. Understandably, there has been a move toward additive manufacturing (AM) with elastomers. This work proposes a new approach to AM with liquid latex, using a drop-on-demand (DoD) based inkjet to fabricate latex patterns. The printhead actuator benefits from a higher material compatibility compared to conventional inkjet/extrusion-based printers, allowing the jetting of viscous fluids, as well as liquids with high solid loading. The setup allows printing with viscous liquid latex of a high solid content (60 wt. %). The process is controllable and reliable, making the printing of patterns possible. In addition, we explore printing with micronized rubber powder (MRP) made from end-of-life tires, to test solid-particle loading compatibility and as a novel method for rubber recycling. In this study, we demonstrate that large-scale DoD inkjet printing is capable of handling solid particle loadings of up to 10 wt. % in addition to the high solid content liquid latex. Moreover, multilayer objects were created from pure liquid latex, as well as from MRP/latex suspensions. Material characterization indicates that the stiffness of cured latex is not altered by the addition of MRP, but reduces the maximum elongation length from 750% to 430%. The results highlight the ability to print with both high particle loading and large particles. This explorative study demonstrates the potential of AM processes with liquid latex, as well as a new approach to tire rubber reuse.

Keywords: 3D printing, rubber, latex, recycling, multimaterial printing, drop-on-demand

Introduction

RUBBER AND ELASTOMERS are widely used materials in industry¹ owing to their advantageous physical properties; good chemical and structural stability, heat resistance and thermal insulation capability, and high strength to weight ratio.² Traditional manufacturing with elastomers is often done by molding and casting. This process allows for little design flexibility and permits mass production but is not flexible to produce one-off products. As such, there has been a move toward developing additive manufacturing (AM) techniques for elastomer/rubber production. For example,

thermoplastic elastomers have been fabricated using laser sintering^{3–5}; however, the resultant structures were found to have reduced mechanical properties compared to rubber objects fabricated through the conventional route. Liquid silicone elastomers have been printed using extrusion based methods,⁶ but this method cannot be applied to a wide range of elastomers due to the restrictions in viscosity.

An alternative AM method for liquid elastomers is drop-on-demand (DoD) inkjet printing. DoD inkjet printing allows droplets to be ejected onto a substrate and subsequently cured. Droplets are conventionally placed adjacently to each other to allow them to coalesce and form a uniform straight

School of Engineering and Materials Science, Queen Mary University of London, London, United Kingdom.

*Co-first authors.

Opposite page: Additive manufacturing with liquid latex. *Photo Credit:* M.A. Quetzeri-Santiago, C.L. Hedegaard and J.R. Castrejón-Pita.

© Miguel A. Quetzeri-Santiago *et al.* 2019; Published by Mary Ann Liebert, Inc. This Open Access article is distributed under the terms of the Creative Commons License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

array. The z-axis definition is created by overlaying layers, with intermittent curing or crosslinking steps to ensure adequate support of subsequent layers.

In DoD printing, a pressure pulse induced by thermal, piezoelectric, or acoustic actuation causes a liquid droplet to form and jet from the printhead nozzle. DoD has a number of advantages above other AM technologies; first, there is no substrate contact, avoiding contamination of the nozzle, and second, higher printing speeds can be achieved compared with, for example, fused deposition modeling (FDM).⁷ Moreover, DoD methods allow a greater control and variability of the droplet volume and speed.^{8,9} In addition, it is a digital technology with great flexibility that naturally permits personalization and one-off production. Unfortunately, material compatibility is an issue in commercial inkjet systems as the technology is restricted to operate under a narrow window of liquid viscosities.

Recent advances in the field include examples of the rubber latex being successfully printed using inkjet; Raza *et al.* used a commercially available MicroFab printhead to print low melting point alloys and elastomers,¹⁰ and Lukić *et al.* printed diluted liquid latex (35 wt. % solid content) with a commercially available piezoelectric inkjet printer.⁵ While these examples show that progress has been made, the techniques still suffer from similar limitations in ink viscosity, solid content, nozzle clogging, and agglomeration. In addition, inks used in AM methods have additional requirements to that of deposition resolution, as droplets are required to cure or solidify fast and leave an adequate footprint to build definition in the z-axis. These restrictions still need to be addressed to improve three-dimensional (3D) printed objects made from viscous or high solid content materials such as bio-gels, conductive inks, and liquid latex.

From the limitations in DoD printing, solid particle loading is one of the main limitations across all inkjet industries. The industry standard for conventional inkjet is a maximum viscosity of 20 cP with a solid loading of <10% per volume and a particle diameter of no greater than 1/20 of the nozzle diameter.^{5,7,11,12} While being able to inkjet undiluted liquid latex is an interesting prospect in itself, the ability to add solid particles to form a colloidal ink widens the market applications for this technique. The addition of particles can be used to reinforce the positive mechanical properties or improve other properties such as thermal and electric conductivity, stiffness, or elasticity of a given construct. Moreover, this includes the possibility of reusing discarded rubber materials, in the form of micronized rubber powder (MRP), in the manufacturing of new products.

In recent years, there has been a move toward producing MRP from waste materials such as tires. Tires remain a major source of waste, despite an increase in governmental initiatives to promote their recycling. In the United States alone there are still 67 million tires occupying landfills, and an estimate of 25% (2010) of all end-of-life tires is placed into landfills worldwide.¹³ Currently, a mere 10% of end-of-life tires are recycled to create new products.¹³ A reason for the low rate is the lack of suitable recycling methods and the limited ability to make new products with discarded material. MRP has proved to be environmental friendly as it can be obtained mechanically with no contaminants released to the environment. The benefits, in terms of cost, have been

previously demonstrated for manufacturing with MRP, to create molded and extruded products.^{14–17}

In this study, we propose to inkjet print with liquid latex, with and without MRP, as a step toward cheaper mold manufacturing with elastomer/rubber based materials. We introduce a versatile DoD inkjet printhead capable of printing pure liquid latex containing a 60 wt. % solid content and a liquid viscosity of 21.8 ± 0.2 cP. Moreover, we explore the concept of creating hybrid MRP/latex constructs using colloidal inks of latex and MRP. Our results show that, in this instance, the inclusion of MRP does not affect the stiffness of the cured product. Finally, we demonstrate that this ink can be used to manufacture cured latex patterns by DoD deposition and natural curing.

Materials and Methods

Ink composition

Two types of ink formulations were used in this study; pure liquid latex and liquid latex with a suspension of rubber tire waste or fine rubber powder (parlon powder). Pure liquid latex was acquired from Liquid Latex Direct, United Kingdom. The liquid latex contains 60% natural rubber, 40% water, and <0.3% ammonia. The density was measured to be $940 \pm 50 \text{ mg} \cdot \text{mL}^{-1}$ and the viscosity to 21.8 ± 0.2 cP. Suspensions were made using parlon powder and thereafter with a coarse rubber powder made from end-of-life rubber, namely, MRP. Suspensions were made by dispersing the parlon powder or MRP in undiluted liquid latex. The weight percentage of suspended MRP or parlon powder was calculated as " $W_{\text{MRP}}/(W_{\text{L}}+W_{\text{MRP}})$ " or " $W_{\text{P}}/(W_{\text{L}}+W_{\text{P}})$ ", where W_{MRP} , W_{P} , and W_{L} refer to the weight of MRP, parlon powder, and undiluted liquid latex, respectively.

Synthetic white parlon powder was purchased from ION-XIA, United Kingdom (~66% chlorine and <2.5% toluene), and MRP was kindly provided by Artis UK. A heterogeneous mixture of MRP was used with a maximum particle size of 0.6 mm. Parlon powder was suspended at concentrations of 3.5 to 6.7 wt. %. MRP was suspended at the concentration 9.6 wt. % when used for printing. Mechanical testing was carried out on cast and cured latex samples containing MRP at concentrations of 0, 5, 9, and 16 wt. %.

Printhead design

For our experiments, two printhead designs were used. These were manufactured in-house and use loudspeaker as actuators. In both systems, the actuator, driven by a pulse generator, pushes the liquid through the nozzle to create a droplet. The printheads are fed with fresh ink through an attached syringe which in turn is attached to a fast-acting meniscus controller (Inca Digital Printers Ltd., United Kingdom) used to balance the pressure inside the printhead and the atmospheric pressure, keeping the meniscus pinned at the nozzle. In this manner, a single pulse of pressure generates a single drop.

Two printhead sizes were used to assess their performance with the colloidal inks. The small printhead uses a 20 mm diameter loudspeaker (8 Ohms, 0.1 W), has an inner liquid reservoir volume of 4 mL, and a conical nozzle with an outer diameter of 1.0 mm. The larger printhead uses a Visaton Structure-Borne Driver loudspeaker (8 Ohms, 25 W) with a

9 mL volume reservoir and a 0.85 mm conical nozzle. We claim that these drivers (loudspeakers) have more actuation power than other piezoelectric driven printheads, for example, MicroFab and MicroDrop, making the printing of high viscosity liquids a reality. The driving signals on both systems are produced using a TTi pulse generator, an acoustic amplifier, and recorded by a digital oscilloscope. The waveform is kept to a single pulse, with control over the pulse amplitude and width, to adjust the droplet speed and size. These printhead designs are further developments (miniaturization and simplification) of a system presented elsewhere.¹⁸

Experimental setup

The small printhead was mounted on to a two-dimensional motorized stage, while the substrate (Kodak inkjet paper) was secured to a support at a fixed distance. In contrast, the larger printhead was fixed to a vibration damped support and the substrate mounted onto the stage (Fig. 1a). The printing distance, that is, the distance from the printhead to the substrate, was kept constant at ~ 5 mm for both systems.

The stages were operated by stepper motors and controlled by the Grbl protocol (open source software for computer numerical control). In brief, the Grbl code transforms a digital structure into coordinates and a series of orders that control the motion of the stepper motors and trigger the jetting of the printhead. The jetting trigger activates (gated mode) the pulse generation signal that is sent to the speaker to print on demand. The Grbl properties, stepper speed, and printing frequency were adjusted to obtain a placement resolution below ~ 300 μm . Both meniscus controllers were set to a negative pressure in the range of 8–9 mm H₂O to keep the meniscus pinned at the nozzle and avoid flooding.

Three-dimensional printing technique

The following procedure was followed for printing; initial loading of printhead and syringe followed by adjusting the backpressure. The driving signal for droplet formation was adjusted in terms of pulse duration and intensity for each ink composition. The printing speed and frequency could be adjusted for each ink and system so that droplet placement

FIG. 1. Printing with liquid latex. (a) The experimental setup showing the Grbl controlled stage and the printhead mounting (the 9 mL reservoir printhead is shown); (b) an example of a single layer structure made from pure liquid latex, using a droplet interval of 2.5 s with two close-ups of the corner resolution; (c) varying the droplet interval keeping the pulse signal and nozzle diameter constant: from left to right increasing the interval length from 1.0 to 5.5 s (inserts show bird-eye perspective). All scale bars 1 mm.

could coalesce and form a continuous line or form a string of equally spaced separated droplets. Two-dimensional patterns were created by controllably printing on the substrate, and 3D constructs were attempted by overlaying consecutive printing layers. Two methods of drying were tested as follows: (1) ambient air curing where individual ~ 1.0 mm width layers take up to 4 min to solidify and (2) blowing hot air ($\sim 400^\circ\text{C}$ from a 2.3 W heat gun) onto the individual print layers for 10 s to achieve curing of the pattern surface.

Imaging

Air-dried constructs and ink samples were imaged using standard bright field microscope from Leica Instruments (Leica MZ12.5 Stereomicroscope with an external light source Leica CLS150X). All standard microscopy images were analyzed using the software ImageJ, with at least five measurements taken per determined value (e.g., construct and droplet dimensions).

Material characterization

An indentation test was run on cast samples (Fig. 2e) containing varying concentrations of MRP (0, 5, 9, and 16 wt. %) to determine the effects of rubber on the material stiffness. Three different samples per concentration were tested, with two to three tests on each sample, hence a minimum of eight tests per concentration. The Young's modulus, E , was derived from the resulting force-displacement data.

Tensile testing was carried out on printed pure liquid latex samples (one layer and four layer), as well as on cast latex samples containing varying amounts of MRP (0, 5, 9, and 16 wt. %). All samples tested were of a rectangular shape. The experiments were carried out on an Instron 5566 UTM with a ± 100 N static load cell and a constant strain rate of 30 mm/min. The tensile stress and strain at the breaking point were determined from the data, as well as the Young's modulus. A minimum of two samples were tested per concentration. All geometries for the tensile test and the values for the obtained strain, stress, and Young's modulus can be found in Table 1. Representative stress-strain plots are shown in Figure 3. Statistical analysis was carried out using the software GraphPad Prism 5. A one-way analysis of variance was used, and a statistical significance was accepted when $p \leq 0.05$.

Results and Discussion

Inkjet printing with liquid latex

Initial tests were focused on establishing reliable printing conditions with pure liquid latex, evaluated in terms of droplet formation and reproducibility, as well as jetting stability over time. Pulse signals were adjusted by changing the pulse width and voltage, to obtain fully formed droplets and avoid satellite droplets.¹⁹ Conical nozzles were used in both printing systems, leading to droplets of uniform size both in-flight and postimpact.

We have previously shown that our systems can produce droplet speeds in the range of $0.5\text{--}2.0\text{ m}\cdot\text{s}^{-1}$, where droplet creation was dependent on the ink properties, the nozzle geometry, and the signal voltage and width.¹⁸ Repetition rates were restricted by the nozzle refilling time, that is, the time taken by the meniscus controller and surface tension to

"fill" the missing/jetted liquid at the reservoir. Given the high viscosity of the liquid latex, a droplet deposition rate (linear printing speed) of $0.15\text{ cm}\cdot\text{s}^{-1}$ was used. Our results indicate that latex droplets produce a footprint (printing dot size) of twice its original diameter, that is, a droplet from a 1.0 mm nozzle produces a circular dot footprint of a 2.2 ± 0.9 mm diameter. Within a range, the droplet size can be adjusted by modifying the pressure pulse width and amplitude, without having to change the nozzle diameter. Both printheads were shown to be capable of jetting pure liquid latex, obtaining consistent jetting with liquid latex containing 60 wt. % solid content and of relatively high viscosity (21.8 ± 0.2 cP).

In conventional DoD printing, often a critical droplet spacing is defined by which the droplets are close enough to coalesce forming a parallel sided line. Above and below the critical spacing, either bulging of the line or no coalescence occurs, respectively.²⁰ Figure 1c shows the range of droplet intervals tested, keeping the motor speed and nozzle diameter constant. As evident, the deposited latex droplets remain isolated (uncoalesced) at droplet jetting intervals greater than 2.5 s, while reducing the interval to ≤ 2.5 s leads to droplet coalescence and path formation. At smaller droplet jetting intervals, the increased overlap leads to instability and bulging.

Under our jetting conditions, continuous printing of pure liquid latex was shown to be consistent and reliable over periods of up to 1 h. Figure 1b shows the left side of a square pattern fabricated with the larger printhead and using a droplet jetting interval of < 2.5 s. These vertical and horizontal lines demonstrate the accuracy and stability of the print. The two close-ups seen in Figure 1c show examples of the achievable resolution at the corners. Printing at corners was controlled by adding a gap at the turning point to minimize bulging from the potential three-way droplet coalescence, that is, the corner droplet, and the neighboring droplets in the horizontal and vertical direction.

Curing at the nozzle is an important limitation for inkjet printing. While a small nozzle is desired to produce small drop sizes that dry fast, a small sessile meniscus can cure itself at the printhead during idle times. In fact, we observed cured menisci blocking nozzles within minutes of stopping printing. In our experiments, cleaning the nozzle plate with a fiber-free swab was sufficient to unblock the meniscus. In a commercial application, nozzle unblocking can potentially be done by flushing out the cured meniscus before printing.

Colloidal constructs and inks

In AM, a degree of versatility in the ink composition is often needed to meet the end product specifications. Ink formulation normally relies on the addition of solid particles to alter the properties of the end product, such as reinforce the material strength and durability or to add color using pigments. Restrictions in solid particle loading is a well-known problem in inkjet technology, with conventional printing inks containing < 10 wt. % solid residue.⁸ Having already shown that the developed system is capable of printing with pure liquid latex of a high solid content, the next step was to prove the feasibility of printing with a suspension of undiluted liquid latex with the addition of either parlon powder or MRP (colloidal ink suspension). The test was designed to include MRP made from end-of-life tire waste.

FIG. 2. Liquid latex with rubber particle loading. (a) Time-lapse of the printhead mounted to the x/y stage, jetting pure liquid latex (1 drop/1.5 s) (scale bar 1 mm); microscopy images of liquid latex with (b) 3.5 wt. % and (c) 6.7 wt. % parlon loading; (d) a defined array made by jetting liquid latex containing 6.7 wt. % parlon powder; (e) cast rubber samples of pure liquid latex and with increasing MRP loading (5, 9, and 16 wt. %); (f) a graph of Young's Modulus, determined using indentation and tensile testing, of cast samples with 5, 9, and 16 wt. % MRP (control; 0 wt. % MRP), and printed samples of one and four layers (1LP and 4LP, respectively) (control thin: a pure latex cast). Data reported as mean $\pm$ standard deviation; (g) example of elongation of a one layer printed sample (1LP) under a constant strain tensile test (insert: original sample) and (h) tensile stress and strain at breaking point, derived from the constant tensile strain experiments ($p < 0.05$). Data reported as mean $\pm$ standard deviation. MRP, micronized rubber powder.

MRP is a heterogeneous mixture of rubber and is comparatively crude. As such, preliminary experiments were carried out using fine parlon powder, which has a very narrow size distribution and an average particle size in the nanometer range. Colloidal ink suspensions of 3.5 and 6.7 wt. % parlon powder were prepared and tested in the printhead. In both instances, consistent jetting was observed (e.g., shown in Fig. 2a).

The printing of the rubber particle and latex ink was demonstrated by jetting a series of defined arrays as seen in

Figure 2a and d. The parlon powder remained suspended in solution throughout the duration of printing, as observed through the printed droplets and when inspecting the leftover ink postprinting. The quality of the parlon distribution postprinting was analyzed using microscopy imaging. The parlon powder was shown to aggregate in the suspension (Fig. 2b, c) leading to a nonuniform size distribution of the suspended particles. However, the parlon was shown to be well distributed within the ink, such that all droplets contain a homogenous mixture of liquid latex and parlon powder.

TABLE 1. SUMMARY TABLE OF THE SAMPLES USED FOR TENSILE TESTING AND THE DETERMINED STRAIN AND STRESS VALUES AT THE BREAKING POINT

	L_0 (mm)	W (mm)	T (mm)	Strain at failure (mm/mm)	Stress at failure (MPa)	Young's modulus ^a (MPa)
Control (0 wt. %)	2.3 ± 0.6^b	8.2 ± 0.5^b	0.5 ± 0.1^b	75.1 ± 3.1	7.9 ± 0.1	2.7 ± 0.2
5 wt. %				51.5 ± 24.3	7.51 ± 2.1	2.1 ± 0.5
9 wt. %				48.5 ± 6.9	7.68 ± 1.9	2.4 ± 0.4
16 wt. %				48.1 ± 1.9	5.44 ± 2.0	2.5 ± 0.7
Control thin	5.9	1.0	0.2	—	—	1.6
One layer print	2.3 ± 0.3	1.9 ± 0.2	0.3 ± 0.3	43.4 ± 5.7	13.5 ± 2.1	1.5 ± 0.1
Four layer print	2.1 ± 0.5	3.5 ± 0.2	1.0 ± 0.1	55.3 ± 4.9	5.8 ± 0.1	4.0 ± 0.8

All values reported are mean $\pm$ standard deviation.

^aThe Young's modulus is reported as the average from the indentation and tensile tests.

^bThese values represent the mean value for control, 5, 9, and 16 wt. %.

Having shown that a solid loading of fine rubber powder is feasible, our experiments then focused on the jetting of coarse recycled MRP, which is of greater commercial interest due to its recycling potential. The MRP used has an average particle size of 0.6 mm, comparatively larger than the parlon powder but with a narrow size distribution. The parlon powder experiments were repeated using a 9.6 wt. % MRP particle loading.

A uniform droplet size was observed throughout each print, although unlike parlon powder, a nonhomogenous distribution of MRP was visible postcuring. Solid tire rubber could be clearly visualized in $\sim 90\%$ of the droplets. The nonuniform distribution of MRP can be attributed to two factors; similar to parlon powder, the MRP tended to aggregate in solution creating large clusters, and second, due to the weight of coarse MRP they were more prone to settle on the bottom of the printhead. This issue is common to all colloidal ink suspensions and not a property specific to the liquid latex system. In fact, many commercially available printheads

continuously recirculate the ink within the printhead to avoid aggregation and clogging the nozzles.^{21,22} Implementing a more defined and rigorous mixing procedure or using smaller particles⁷ could mitigate agglomeration of the particles in solution, as well as reducing the observed settling in the printhead. Alternatively, gentle vibration of the printhead reservoir could be introduced.

The impact on the mechanical properties was tested for a range of MRP particle loadings. Samples were prepared using casting, as shown in Figure 2e, with a range of 0 to 16 wt. % MRP solid content. The samples were tested by the standard indentation and constant strain tensile tests. The two experimental methods yielded comparative values for the Young's Modulus (the overall mean $\pm$ standard deviation is reported in Table 1). The results indicate that the stiffness of these materials is not greatly affected by the colloid content, and any differences are within error of each other and not statistically significant (Fig. 2f). However, the tensile test

FIG. 3. The stress-strain plot for the samples “one layer print (1LP),” “four layer print (4LP)” and “control” (pure latex). All data points are reported as the mean $\pm$ standard deviation.

indicates that adding MRP to the latex reduces the maximum elongation length from 750% to 480% (Fig. 2h, strain at failure). The ultimate tensile stress (stress at the breaking point) was found to be equal, within error, for all four sample types (Fig. 2h, stress at failure).

Having determined the impact of MRP on the mechanical properties, next the effect of printing was tested. Two types of printed pure liquid latex samples were tested, namely, a one layer and a four layer printed rectangle. An example of the one layer print being tested is shown in Figure 2g. The stress-strain plots are shown in Figure 3. First, in terms of stiffness a higher Young's modulus was observed in the case of four layers compared with one layer. However, in both instances the printed samples yield similar Young's modulus to the cast controls. The one layer printed line (Fig. 2g, h) was elongated by $434\% \pm 60\%$ before breaking, whereas the four layer printed line (four layers printed overlaying each other) was elongated by $553\% \pm 50\%$ (Fig. 2h). The one layer print showed a higher ultimate tensile stress compared to the four layer print (statistically significant).

Overall, we can conclude that the droplet-to-droplet and layer-to-layer bonding in the printing do not significantly change the mechanical properties of the latex; however, there is a clear dependency on sample thickness as seen in the difference of the ultimate tensile stress. Combining these results, we infer that the effect of MRP particles in latex reduces the elasticity without affecting the stiffness of the printed samples. This is in line with other works, such as Mueller *et al.* in 2017, that have established that the global and local mechanical properties of inkjet manufactured parts can be affected in manufactured mixed-material parts.²³

We have demonstrated the ability to print high solid content latex and with suspended recycled rubber, which from an AM perspective brings new possibilities to the recycling potential of rubber tire waste. There is a growing market for commercial AM, with many areas of industry yet to take full advantage of this evidence.²⁴ Currently, asphalt and concrete applications where most end-of-life tires are used or recycled, a maximum of 20 wt. % of rubber is used.^{25,26}

In this article, the final 3D printed objects have ≈ 10 wt. % of rubber from tires. However, in contrast to other recycling methods, 3D printing offers a more versatile way of recycling. Despite having an arguably low quantity of MRP in our ink, this technique can be used in the manufacture of commonly used items, such as, for example, smartphone cases, in which the market capacity would significantly increase the quantity of recycled rubber per annum. Another possibility is the printing of thermal insulation for circuits or protective coatings on electronic components. Moreover, the system has room for incrementing the rubber tire contents, for example, using finer MRP and/or by diluting the liquid latex.

An untested AM option to include a higher MRP content in the final product can be to print latex on a powder bed 3D printing mode, whereby the liquid latex is used to bind the recycled rubber powder on the bed. In this instance, the MRP would have to be sufficiently fine milled in order for the binding to occur. This method was briefly explored in this study, but a purpose build stage would be needed to achieve high-resolution constructs. Other alternative AM techniques, such as FDM or fused filament fabrication, are not suitable for manufacturing with tire rubber, as tire rubber does not "fuse" to produce a continuous extruded filament.⁵

The system requires further development and optimization to be a solution to the tire waste problem; however, this is the first step toward that goal.

Transition to 3D objects

Having shown that it is possible to print reliably with liquid latex, as well as shown the feasibility of using a colloidal ink along with the added material benefits, next the possibility of creating 3D objects was explored. Initially precision and resolution of the system were determined. In the first instance, pure liquid latex was used.

The first patterns created were circles with a diameter of 22 mm (Fig. 4a–c), with a droplet interval of 2.5 s to produce a continuous string formation. Three consecutive layers were completed with intermittent hot air blowing allowing each layer to semidry before applying the next layer. As previously described, two approaches to drying were tested; first, drying under ambient air conditions resulting in 4 min drying time for a ~ 1.0 mm width layer.

The second method consisted in blowing hot air ($\sim 400^\circ\text{C}$) onto the individual print layers for 10 s to achieve a fast curing of the pattern surface. The print resolution was reduced with increasing layers as evident by the increase in width. This can, for example, be seen in Figure 4a and b, where the wall thickness of the circular pattern increases from 1.7 ± 0.2 mm at layer 1 to 2.6 ± 0.2 mm at layer 3. This effect is also the result of the drying/curing speed as the droplet cures into a spherical cap and not as a pancake shape as in other applications of 3D printing. However, the initial couple of layers retain the precision of the coordinated stage movement and droplet formation, showing that high resolution is achievable. Connecting interfaces were visualized using bright field microscopy. Individual droplets were clearly visualized, showing the layered structure of droplets in the constructs, originating from stepwise layering (Fig. 4c). Increasing the speed of drying between layers would increase the resolution retention.

A star pattern (Fig. 4d, e) was made using a $100 \text{ mg} \cdot \text{mL}^{-1}$ (9.6 wt. %) MRP suspension. The construct thickness measured 1.9 ± 0.4 mm and was made from 15 overlaying layers (Fig. 4f). Droplets were in this instance placed adjacent, but not overlapping in an attempt to mitigate the pronounced bulging instability as observed with increasing layers.²⁷ While finding the critical droplet spacing is the norm in other 3D inkjet-based printing, in our case the droplets are one order of magnitude larger than conventional DoD. As such, a greater level of precision is potentially achievable when the droplets are kept adjacent without coalescing, allowing for each layer to dry in "droplet" shape. Improving the overall resolution would mean decreasing the nozzle diameter from mm to μm and, thereby, increasing control and precision. Smaller DoD systems, such as MicroFab print-heads, were available but not tried as the risk of blocking was very high given the size of particles, the high bulk viscosity, and the risk of curing at the nozzle.

Postdrying the construct revealed an increased aggregation of MRP particles in the pattern, visible as distinctive black patches (Fig. 4d, e). At the corners (Fig. 4e), the printing resolution also decreases going from an angle of $42^\circ \pm 2^\circ$ to $52^\circ \pm 3^\circ$, meaning that sharpness of each corner is decreased with increasing layers.

FIG. 4. Three-dimensional latex constructs. (a) Three layers of pure liquid latex in wet and (b) dry state, with (c) close-ups of the layer structure; (d) a three-dimensional star construct made from liquid latex with 100 mg/mL (9.6 wt. %) MRP, with (e) close-up of the dotted area in d and (f) a side view; (g) a more complex one layer structure made from pure liquid latex and (h) close-ups of the dotted areas in g showing the corners and line width.

Finally, more complex one-pass printing patterns were attempted using pure liquid latex. Figure 4g and h demonstrates the ability of our technique to create more complex structures, while retaining good placement resolution. Zooming in on the connection points (Fig. 4h) evidences that while a clearly defined three-way corner is possible (top and bottom left), bulging can still occur from three-way coalescence. Further fine-tuning of the meshing GRBL/G-code instructions at the corners can remove this problem by reducing jetting at the corners. While the fluid properties and curing mechanisms require further development to decrease the time of solidification, our results show that single or few layer printing is achievable.

Conclusion

In this article, we introduce an inkjet-based AM process capable of printing with liquid latex with up to 60 wt. % solid content and a liquid viscosity of 21.8 ± 0.2 cP, both signifi-

cantly higher than previous printing methods. Moreover, this system is able to print with a mixture of liquid latex and tire rubber particles of 0.5 times the nozzle diameter. Multiple layer objects were fabricated with pure liquid latex, as well as with liquid latex with the addition of MRP. The Young's modulus, as well as the strain at the breaking point, showed no change when adding the MRP while maximum elongation length is reduced. Moreover, the printing process does not affect the Young's modulus of the objects. The capability of printing with a high particle loading (high solid content latex with the addition of parlon powder or MRP) and a heterogeneous particle size distribution shows that the printhead design can operate in a wide range of solid particle loadings. This is a great advance, as most conventional inkjet-based 3D printers cannot operate with viscous liquids or liquids with solid particle loading.

The study has demonstrated the potential of AM with liquid latex; however, there is still scope for improvement. For example, the drying time of the liquid latex should be

shortened further, by, for example, including a heating source in the stage or in the printing bed. Improvement of the stage and pattern control would enhance the resolution and reliability of the print quality. A reliable method of AM with liquid latex would bring great merits to the industry, by reducing cost of manufacturing (no molds needed) and adding an unprecedented degree of flexibility in the manufacturing process. Moreover, the study has highlighted a novel method of recycling end-of-life tires. With this work, it is foreseeable that in the future we can create 3D printed objects with rubber tire waste, expanding the current recycling and waste management methods.

Acknowledgments

M.A. Quetzeri-Santiago acknowledges the funding from the Mexican Energy Ministry (SENER) and the National Council for Science and Technology (CONACYT) Mexico. The authors thank Artis UK for providing the micronized rubber powder. We thank Finn Box from the University of Oxford for his support with the indentation tests and Karen Silva Blankenagel from Queen Mary University of London for her support with the tensile tests.

Author Disclosure Statement

No competing financial interests exist.

References

- Barlow C, Jayasuriya S, Tan CS. *The World Rubber Industry*. London, UK: Taylor & Francis, 2014.
- Corporation Woodland Plastics. *Understanding Thermoset Plastics*. Published 2015. www.woodlandplastics.com/understanding-thermoset-plastics.html, Accessed June 25, 2018.
- Goodridge R, Tuck C, Hague R. Laser sintering of polyamides and other polymers. *Prog Mater Sci* 2012;57:229–267.
- Kruth JP, Levy G, Klocke F, *et al.* Consolidation phenomena in laser and powder-bed based layered manufacturing. *CIRP Ann Manuf Technol* 2007;56:730–759.
- Lukić M, Clarke J, Tuck C, *et al.* Printability of elastomer latex for additive manufacturing or 3D printing. *J Appl Polym Sci* 2015;133:42931.
- Duoss EB, Weisgraber TH, Hearon K, *et al.* Three-dimensional printing of elastomeric, cellular architectures with negative stiffness. *Adv Funct Mater* 2014;24:4905–4913.
- Guo Y, Huseini SP, Bogner B, *et al.* Rapid Prototyping Journal Inkjet and inkjet-based 3D printing: Connecting fluid properties and printing performance. *Inkjet and inkjet-based 3D printing: Connecting fluid properties and printing performance*. *Rapid Prototyp J* 2017;23:562–576.
- Castrejon-Pita JR, Baxter WRS, Morgan J, *et al.* Future, opportunities and challenges of inkjet technologies. *At Sprays* 2013;23:541–565.
- Castrejon-Pita AA, Castrejon-Pita JR, Martin GD. A novel method to produce small droplets from large nozzles. *Rev Sci Instrum* 2012;83:115105.
- Raza I, Iannucci L, Curtis PT. Introducing a multimaterial printer for the deposition of low melting point alloys, elastomer, and ultraviolet curable resin. *3D Print Addit Manuf* 2017;4:83–89.
- Derby B, Reis N. Inkjet printing of highly loaded particulate suspensions. *MRS Bulletin* 2003;28:815–818.
- Hon KKB, Li L, Hutchings IM. Direct writing technology—advances and developments. *CIRP Annals* 2008;57:601–620.
- Forrest, M. *Recycling and Re-Use of Waste Rubber*. Shropshire, UK: Smithers Rapra Technology Ltd., 2014. ISBN: 978-184735-682-6.
- Rubber Manufacturers Association. *Scrap Tire Markets in the United States, 9th Biennial Report*. Washington, 2009.
- Aranda Uson A, Ferreira G, Zabalza Bribian I, *et al.* Study of the environmental performance of end-of-life tyre recycling through a simplified mathematical approach. *Therm Sci* 2012;16:889–899.
- Kind RC. The use of tyre crumb as a major ingredient in retread compound. In: *Proceedings of RubberCon*. Manchester, United Kingdom, 2014.
- Rosenmayer T, Ayyer R, Papp F. Characterization of Micronized Rubber Powders with cost effective performance benefits in rubber compounds. In: *Annual Technical Conference—ANTEC, Conference Proceedings*, 2012.
- Castrejon-Pita JR, Martin GD, Hoath SD, *et al.* A simple large-scale droplet generator for studies of inkjet printing. *Rev Sci Instrum* 2008;79:075108.
- Derby B. Inkjet printing ceramics: From drops to solid. *J Eur Ceram Soc* 2011;31:2543–2550.
- Derby B. Inkjet printing of functional and structural materials: Fluid property requirements, feature stability, and resolution. *Annu Rev Mater Res* 2010;40:395–414.
- Matsumoto Y, Kobayashi N, Kawamura H. Liquid discharge head and recording device. KYOCERA Corp, 2017. U.S. Patent Application 15/128,263.
- Brook C, Ristea A, Walsh M, *et al.* Droplet deposition apparatus and method for manufacturing the same. Xaar Technology Ltd, 2017. U.S. Patent 9,566,786.
- Mueller J, Courty D, Spielhofer M, *et al.* Mechanical properties of interfaces in inkjet 3D printed single- and multi-material parts. *3D Print Addit Manuf* 2017;4:193–199.
- Gordon R. Trends in commercial 3D printing and additive manufacturing. *3D Print Addit Manuf* 2015;2:89–90.
- Mashaan NS, Ali AH, Karim MR, *et al.* A review on using crumb rubber in reinforcement of asphalt pavement. *Sci World J* 2014;2014:1–21.
- Cetin A. Effects of crumb rubber size and concentration on performance of porous asphalt mixtures. *Int J Polym Sci* 2013;2013:1–10.
- Stringer J, Derby B. Formation and stability of lines produced by inkjet printing. *Langmuir* 2010;26:10365–10372.

Address correspondence to:

J. Rafael Castrejon-Pita
School of Engineering and Materials Science
Queen Mary University of London
Mile End Road
London E1 4NS
United Kingdom

E-mail: castrejon@cantab.net